

# Europox Z Slow

## Packaging:

**2 components: 10,20,30 kg**

**Component A: 20 kg**

**Component B: 10 kg**

## Properties:

- **Close to 100% solid, solvent-free**
- **Low viscosity**
- **High adhesive strength**
- **Easily processable**
- **Very good pore filling capacity**
- **Density (g/cm<sup>3</sup>) primer = 1**
- **Electrical conduction > 100 G  $\sigma$ .**
- **Viscosity m<sup>2</sup> (mPa.s) primer 750-1500**
- **Adhesive strength (N/mm<sup>2</sup>) > 1,5 (concrete fracture)**
- **Shore hardness > D80**

## Description:

**Europox Z Slow is a solvent free two part epoxy primer. Europox Z Slow has great adhesive qualities for normal to strong absorbent porous substrates and is the recommended primer for porous cementitious substrates such as normal concrete and cement screeds.**

**Substrate:**

The substrate must be clean and dry and free of dirt, oil, grease and any other impurities or contaminants.

The substrate must be sound and sufficiently compression resistant (at least 25 N/mm<sup>2</sup>), with a minimum adhesive strength of 1,5 N/mm<sup>2</sup>.

Weak concrete must be removed, and surface damage such as blowholes and voids must be repaired with Sealer E and then primed again. **DO NOT USE POLYESTER PUTTY AS NO ADHESION WILL BE OBTAINED.**

The concrete or screed substrate must be primed.

Uneven substrates must be levelled in order to achieve an even substrate.

Before applying the product, all dust and loose parts must be fully removed, preferably using a brush and or industrial vacuum cleaner.

**Consumption:**

<b>Product</b>	<b>Consumption</b>
<b>Europox Z Slow</b>	<b>125-150 g/m<sup>2</sup></b>

**Application conditions:**

Surface temperature:	Minimum -5°C, maximum +35 °C
Ambient temperature:	Minimum -5°C, maximum +35 °C
Surface moisture content: To be tested with a carbide meter.	< 4 % moisture
Relative air humidity:	Maximum 80% R.H.
Dew point:	Beware of condensation!

The temperature of the substrate and non-hardened material must be at least 3°C higher than the dew point to reduce the risk of condensation, efflorescence or stickiness (carbamate formation) on the floor finish.

**Remark: Low temperatures and high air humidity increase the risk of efflorescence or carbamate formation.**

**Pay attention:**

- Please check if you have the right A + B component
- Mixing is very important. Use the time strictly because otherwise no chemical reaction will take place.
- When applying the material please wear protective clothing and gloves.

**Additional information:****Shelf life / storage:**

Up to 12 months after the production date in the original, sealed, unopened and undamaged packaging, stored dry between + 5 °C and 30°C.

**Mixing:**

Mixing ratio: Component A: Component B = 100 : 50

Add part B to Part A and mix continuously for 2 minutes until a uniform mixture has been achieved

**Application:**

Potlife @ 20°C	45 minutes
Touch-dry @20°C	8 hours
Foot Traffic @20°C	24 hours

**Form:**

Component A: Liquid, coloured

Component B: Liquid, transparent, clear to slightly yellow

Application at different stages and combining different batch numbers in one project could result in a slight colour difference, to avoid this:

Order all materials for your project at the same time.

Discoloration and color deviation can occur, this will not affect the functionality or performance.

**Remarks :**

The most important issue of priming is the filling of all the (micro) pores to avoid air bubbles and pinholes in the wearing course.

Uneven or dirt covered substrates should not be treated with thin coatings. Both substrate and adjacent areas should always be thoroughly prepared and cleaned prior to application.

Protection from rain and water is necessary during processing and hardening.

Wrong assessment and treatment of cracks can result in a reduction of lifespan and recurring cracking.

Mixed materials must be processed immediately as flow and defoaming will be reduced when pot life date expires.

If heating is required do not use gas, oil paraffin or other fossil fuel burners. These produce large quantities of CO<sub>2</sub> and water vapour, which can adversely affect the finish. For heating, only use electrically powered hot air ventilation systems.

**Health and safety information:**

For information and advice on the safe handling, storage and disposal of chemical products, the user should consult the latest product safety data sheet, concerning physical, environmental, toxicological, and other safety-related data.

**Legal Notices:**

The information, and in particular the recommendations regarding the application and end use of Eurostep Poland products, has been provided in good faith, based on our current knowledge and experience regarding the products. They are valid for products that are properly stored, processed and used under normal conditions in accordance with the recommendations of Eurostep Poland. In practice, the differences in materials, substrates and actual conditions on the construction site are so great that there is no guarantee of merchantability or fitness for a particular purpose, and no liability arising from any legal relationship can be inferred from this information, written recommendations or any other advice offered.

The user of the products must verify that the product is suitable for its intended use and purpose. Eurostep Poland reserves the right to change the properties of its products. The property rights of third parties must be respected. All orders are accepted subject to our current terms and conditions of sale and delivery. Users must always refer to the latest edition of the technical datasheet for their product, copies of which will be provided upon request.