

Plex Roadmark CPS

DESCRIPTION:

Plex Roadmark CPS is a fast, 2-component, methacrylate screed with a combination of fillers, anti-skid aggregates and glass beads for reflectivity. It is applied between 1,5 – 3 mm thickness by means of trowel, draw box or hand or automatically driven cold plastic extrusion machines.

The screed can be used for durable and permanent cold plastic roadmarkings like markings at junctions and crossings, stop lines, direction arrows and centre markings on freeways and highways and is also suitable for safety and/or structured road markings.

Plex Roadmark CPS is suitable for warm and cold climates and requires no heating prior to application and has an very good sag resistance allowing for excellent layer build and coverage on new asphalt.

APPLICATION:

Mix the Plex Roadmark CPS briefly before weighing it out. Add the recommended amount of catalyst and mix thoroughly for 1 minute.

Application by trowel

Roughly calculate the amount of compound required based on the square metres of the area. The amount of hardening powder required is adapted to the substrate temperature according to the hardening table shown above and mixed for half a minute (in warm temperatures) to one minute (in cold temperatures). Pour the screed out and smooth it without leaving trowel marks.

Application by drawbox

Prepare the screed as previously instructed. Instead of using a trowel, use a steel draw box, similar to those used for hot-melt materials. Place a strip of masking tape at the starting point of the marking and align the draw box with it. Fill the draw box with the liquid cold plastic, already mixed with the hardener, and pull it along a guide (such as a straight plank, roof batten, or aluminum rail) up to the endpoint. To create an end line, you can use another piece of masking tape, or place a metal sheet to catch any excess material from the applicator head.

Drop On Beads

Drop on beads need to be added immediately after applying Plex Roadmark CPS onto the substrate. Due to its paste-like consistency especially small beads are a good choice for easy embedding. Please make sure that the beads are embedded into the cold plastic mass to about 50 %, to maximize retro reflection as well as bead-adhesion.

A decisive factor for bead adhesion is the proper bead coating. Therefore, only for our own beads we can give a guaranty for a good bead-adhesion.

Ensure sufficient ventilation during installation of the floor. In enclosed spaces, mechanical ventilation with at least 7 air changes per hour is mandatory.

CONSUMPTION:

Coating system	Product	Consumption
Primer	Plex 1120 (only on concrete)	0,5 - 0,8 kg/m ²
<u>Wearing Course</u>	Plex Roadmark Area	<u>1,85 kg/m²/mm</u>

TECHNICAL PROPERTIES:

Excellent hiding power	
Resistant to weathering.	
Suitable for high and low temperatures.	
High luminance and reflectivity	
Excellent resistance to bleeding	
Rapid curing in about 30 min at 25 °C	
Excellent abrasion resistance	
Low dirt retention	
Density:	+/- 1,85 g/cm ³
Processing time 20°C (min)	+/- 15
Viscosity (Pa.s) ¹⁾	10 - 12
Shore D hardness	50-60

¹⁾ Brookfield DVIII SPINDLE LV4 30RPM

PACKAGING:

Can packing: 20 kg
Metal drum: 180 kg

FORM:

Component A: Liquid, coloured
Component B : dry white powder

For a single project, always order all the material at once.

SHELF LIFE:

Up to 6 months after the production date if kept in the original, sealed, unopened and undamaged packaging and stored dry between +5 °C and +30 °C.

CATALYST QUANTITY:

Temp (C°)	Catalyst (%)	Potlife (Min)	Cure time (Min)
0 - 5	4	20	60
5 - 10	3	25	55
10 - 20	2	17	35
20 - 30	1.5	14	30

SUBSTRATE:

Concrete Road Surfaces

Concrete needs to be pre-treated by shot blasting or high-pressure water blasting and primed with Plex 1120.

Asphalt Road Surfaces

Remove incompatible paint systems, sweep surface to remove dust and debris. Depending on the amount of flux oils contained in new bituminous surfaces, these may need to be weathered up to 8 weeks before final application. Especially on hot days sweating of flux oils from fresh bitumen occurs often. If cold plastic material is applied too early on fresh asphalts the cured marking can be peeled off. In case of doubt we recommend applying a test stripe and try to peel it off after curing (30 min). If peeling off is possible then, hot ambient temperatures should be avoided and or the road surface needs additional time to be weathered.

APPLICATION CONDITIONS:

Surface temperature: Minimum 0°C, maximum +35 °C

Ambient temperature: Minimum 0°C, maximum +35 °C

Relative air humidity: Maximum 75% R.H.

Dew point: Beware of condensation!

The material and substrate should be at least 3°C higher than the dew point.

REMARKS:

When applying the material, ensure the correct personal protective equipment is worn.

Prior to use, Plex Roadmark CPS must be carefully stirred to achieve a uniform distribution of agents contained in the product.

Mixed materials should be processed immediately. Don't work from the bucket, empty entire contents. No direct sunlight during application and avoid strong air currents such as drafts.

Other topcoats than based on MMA should not be applied on Plex systems as cracking and delamination can occur.

LEGAL NOTICE:

This information, and in particular the recommendations related to the application and end use of Eurostep products, is provided in good faith based on our current knowledge and experience of the products. It is valid for products that are correctly stored, treated and applied under normal conditions in accordance with Eurostep's recommendations.

In practice, differences in materials, substrates and actual on-site conditions are such that no warranty in respect of merchantability or of suitability for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered.

The user of the products must test the product's suitability for the intended application and purpose. Eurostep reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the technical data sheet for the product concerned, copies of which will be supplied on request.

HEALTH AND SAFETY:

For information and advice on the safe handling, storage and disposal of chemical products, the user should consult the most recent product safety data sheet consult, regarding the physical, ecological, toxicological and other safety-related data.

VALUE BASE:

All technical data stated in this technical data sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

For more information about the Eurostep products or for technical advice, please contact:

Eurostep Poland Sp. z o.o.
Tymiankowa 37/39
95-054 Ksawerów
Poland

Tel.: +48 609 222 050

www.Eurostep.pl