

PLEX 1690 COLOURED

DESCRIPTION:

Plex 1690 is a pigmented polymethyl methacrylate sealcoat for the MMA TF system. This coating is available in all RAL and NCS colors. Due to the excellent UV resistance this is the perfect solution for balconies, terraces and other outside applications. As well as its great resistance for tire imprints.

CATALYST AMOUNT:

Temp. [°C]	Catalyst [%]	Processing time [min]	Curing [min]
0-10	4	~14	35-40
10-15	3	~14	30-35
15-20	2	~12	30-35
20-30	1,5	~11	20-30

CONSUMPTION:

Floor system	Product	Consumption
Top layer	Topcoat Plex 1690 Coloured	~0,650 - 0,950 kg/m ²

SUBSTRATE PREPARATION:

The substrate must be sound and sufficiently pressure-resistant (minimum 25 N/mm²), with a minimum bond strength of 1.5 N/mm².

The substrate must be clean, dry and free of dirt, oil, grease and other contamination. Before applying the top coat, remove excess quartz from the floor and vacuum the floor.

Adding too much catalyst may cause yellow spots because the topcoat will then build up too high a temperature.

APPLICATION CONDITIONS:

Substrate temperature: Minimum 10°C, maximum +35 °C

Ambient temperature: Minimum 10°C, maximum +35 °C

Surface moisture content: < 4% moisture
To be tested with a carbide measurement.

Relative humidity: Maximum 80% R.H.

Dew point: Beware of condensation!

The recommended temperature of the material before application is 20° C.

The material must not be applied if the temperature is lower or equal to the dew point.

APPLICATION:

Briefly mix up the Plex 1690 Colored before weighing. Add the recommended amount of catalyst and mix thoroughly. Note: In case of partial consumption, weigh in the correct quantities. See table below.

Number of kilograms	1% catalyst	1,5% catalyst	2% catalyst
1 kg	10 g	15 g	20 g
5 kg	50 g	75 g	100 g
10 kg	100 g	150 g	200 g
20 kg	200 g	300 g	400 g

Mix the Plex 1690 with the added catalyst 1-2 minutes preferably with a high-powered mixer with a Collomix WK 90 mixing rod at low speed, 300 - 400 RPM.

Apply with a squeegee and re-roll with a coat roller.

Ensure adequate ventilation during application of the product!

FEATURES:

- Good impact and shock resistance
- Very short curing time
- Easy to process
- Good resistance to low temperatures
- Chemical resistance

TECHNICAL PROPERTIES:

Density ² [g/cm ³]	1,084 - 1,152
Viscosity ¹ [mPa·s]	1200 - 1800
Shore Hardness ³	> D60
Tensile strength ⁴ [N/mm ²]	> 20 (sample thickness 3,0 mm)
Elongation at break ⁴ [%]	>10 (sample thickness 3,0 mm)
Bond strength ⁴ [N/mm ²]	> 1,5 (concrete fixture)

1) IKA lo-vi, SP-3, 30 RPM, 20°C

2) ISO 2811-1, + 23°C/50% R.H.

3) DIN 53505, 14 days / +23°C / 50% R.H.

4) ISO 527/+ 23 °C/50% R.H.

PACKAGE:

Tin packaging: 10, 20 kg
Barrels: 180 kg

SHELF LIFE:

Up to 12 months after production date in original, sealed, non-opened and undamaged packaging, stored dry between +10 °C and +30 °C.

NOTES:

Wear appropriate personal protective equipment when applying the material. Protection from rain and water is necessary during processing and curing. Improper assessment and treatment of cracks may lead to recurrent cracking. Mixed materials should be processed immediately. If heating is required, do not use gas, oil paraffin or other fossil fuel burners. These produce large amounts of CO₂ and water vapour, which adversely affect the finish. Use only electrically powered hot-air ventilation systems for heating.

LEGAL NOTICE:

The information, and especially the recommendations regarding the application and end use of Eurostep products, is provided in good faith based on Eurostep's current knowledge and experience with products properly stored, handled and applied under normal conditions. In practice, differences in materials, substrates and actual site conditions may be such that no warranty as to merchantability or fitness for a particular purpose can be derived from this information and advice, nor any liability arising from any legal relationship, based on this information, or from any written recommendations or any other advice given. Eurostep reserves the right to change characteristics of products. The property rights of third parties must be respected. All orders are accepted under the current sales and delivery terms and conditions. Users should always consult the most recent edition of the product safety data sheet for the product concerned. Copies of these will be provided on request.

HEALTH AND SAFETY:

For information and advice on the safe handling, storage and disposal of chemical products, the user should consult the most recent product safety data sheet consult, regarding the physical, ecological, toxicological and other safety-related data.

VALUE BASE:

All technical data stated in this technical data sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

For more information about the Eurostep products or for technical advice, please contact:

Eurostep Poland Sp. z o.o.
Tymiankowa 37/39
95-054 Ksawerów
Poland

Tel.: +48 609 222 050

www.Eurostep.pl