

Europox Z Slow

DESCRIPTION:

Europox Z Slow is a solvent free two part epoxy resin. Europox Z Slow has great adhesive qualities for normal to strong absorbent porous substrates and is the recommended primer for porous cementitious substrates such as normal concrete and cement screeds. Europox Z Slow can also be used as a scratch coat if a calcium carbonate such as Microdol A 100 is added at a mixing ratio of 1:1.

CONSUMPTION:

Consumption depends on the absorbency and flatness of the substrate.

Product	Consumption
Europox Z Slow (1st layer)	0,2 - 0,4 kg/m ²

APPLICATION:

Potlife @ 20°C
25 minutes
Touch-dry @ 20°C
12 hours
Foot Traffic @ 20°C
2 days
Fully hardened @ 20°C
7 days

Check the moisture content of the substrate, the R.H. and dew point before applying the product. Primer and Scratch Coat application: Apply the material evenly on the substrate, using a trowel or squeegee. Europox Z Slow must be overlaid within 48 hours.

SUBSTRATE PREPARATION:

The substrate must be clean and dry and free of dirt, oil, grease and any other impurities or contaminants. The substrate must be sound and sufficiently compression resistant (at least 25 N/mm²), with a minimum adhesive strength of 1.5 N/mm². Weak concrete and loose cementitious levelling must be removed, and surface damage such as blowholes and voids must be repaired with Epoxygel and then primed again. DO NOT USE POLYESTER PUTTY as no adhesion will be obtained. The concrete or screed substrate must be primed. Uneven substrates must be levelled in order to achieve an even substrate. Use Cementitious SL Underlayment or Cementitious SL Constructive. Please see corresponding Technical Data Sheet for more information. Before applying the product, all dust and loose parts must be fully removed, preferably using a brush and/or industrial vacuum cleaner. Concrete substrates must be mechanically prepared using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.

PROPERTIES:

Approx. 100% solid, solvent-free
Low viscosity
High adhesive strength
Easily processable
Alkylphenol-free hardener
Very good pore filling capacity
Density¹ (g/cm³) Primer 1,00
Density¹ (g/cm³) Scratch coat 1,50
Electrical conduction >100 GΩ
Viscosity² (mPa.s) Primer 500 - 750
Viscosity² (mPa.s) Scratch coat 3,500 - 4,000
Adhesive strength³ (N/mm²) > 1.5 (Concrete fracture)
Shore hardness⁴ > D80

1 = EN 12190, 14 days/ + 23 °C/50% R.H
2 = Brookfield, LV4, 30 RPM, @ 23°C
3 = EN 4624, 14 days/ + 23 °C/50% R.H
4 = DIN 53505, 14 days/ + 23°C/50% R.H

PACKAGING:

Component A: 19,98 kg resin
Component B: 10,02 kg hardener
Set: 30 kg (10 and 20 kg available)

FORM:

Component A: liquid, clear
Component B: Liquid, brownish

APPLICATIONS:

- Primer
- Scratch coats
-

Application conditions:

Surface temperature: Minimum 10°C, maximum +35°C
Ambient temperature: Minimum 10°C, maximum +35°C
Substrate moisture content: < 4% damp
To be tested with a carbide meter.
Relative air humidity Maximum 80% R.H.
Dew point: Beware of condensation!

The temperature of the substrate and non-hardened material must be at least 3°C higher than the dew point to reduce the risk of condensation, efflorescence or stickiness (carbamate formation) on the floor finish.

Remark: Low temperatures and high air humidity increase the risk of efflorescence or carbamate formation.

REMARKS:

The most important issue of priming and scratching is the filling of all the (micro) pores to avoid air bubbles and pinholes in the wearing coarse.

Uneven or dirt covered substrates should not be treated with thin coatings. Both substrate and adjacent areas should always be thoroughly prepared and cleaned prior to application.

Protection from rain and water is necessary during processing and hardening.

Wrong assessment and treatment of cracks can result in a reduction of lifespan and recurring cracking.

Mixed materials must be processed immediately as flow and defoaming will be reduced when pot life date expires.

If heating is required, do not use gas, oil, paraffin or other fossil fuel burners.

These produce large quantities of CO₂ and water vapour, which can adversely affect the finish. For heating, only use electrically powered hot air ventilation systems.

LEGAL NOTICE:

This information, and in particular the recommendations related to the application and end use of Eurostep products, is provided in good faith based on our current knowledge and experience of the products. It is valid for products that are correctly stored, treated and applied under normal conditions in accordance with Eurostep's recommendations.

In practice, differences in materials, substrates and actual on-site conditions are such that no warranty in respect of merchantability or of suitability for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered.

The user of the products must test the product's suitability for the intended application and purpose. Eurostep reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the technical data sheet for the product concerned, copies of which will be supplied on request.

HEALTH AND SAFETY:

For information and advice on the safe handling, storage and disposal of chemical products, the user should consult the most recent product safety data sheet consult, regarding the physical, ecological, toxicological and other safety-related data.

VALUE BASE:

All technical data stated in this technical data sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

For more information about the Eurostep products or for technical advice, please contact:

Eurostep Poland Sp. z o.o.
Tymiankowa 37/39
95-054 Ksawerów
Poland

Tel.: +48 609 222 050

www.Eurostep.pl