

PLEX 1310 THIX

DESCRIPTION:

Plex 1310 Thix is a viscous, urethane-modified, pre-reacted 100% solid membrane system based on acrylic monomers. The cured product forms a tough but flexible crack-bridging membrane that maintains its flexibility and performance even at temperatures as low as -20°C.

Thanks to its flexible properties, Plex 1310 Thix is ideal for easy application as tough elastomeric waterproofing and crack-bridging membrane for floors, vertical and inclined surfaces. Ideal for crack repairs.

APPLICATION:

Briefly mix the Plex 1310 Thix before weighing. Add the recommended amount of catalyst and mix thoroughly.

Note: For partial use, weigh out the correct amounts. Refer to the table below.

Amount in kg	2% Catalyst	4% Catalyst	6% Catalyst
1 kg	20 g	40 g	60 g
5 kg	100 g	200 g	300 g
10 kg	200 g	400 g	600 g
20 kg	400 g	800 g	1200 g

Mix the Plex 1310 Thix with the added catalyst for 1-2 minutes, preferably using a powerful mixer equipped with a Collomix WK 90 mixing paddle at a low speed, between 300 – 400 RPM.

Pour the mixed material in strips onto the substrate and spread it using a trowel or squeegee, ensuring that the minimum layer thickness of 1 mm is exceeded. A 1 mm thickness is required to achieve a continuous, uninterrupted resin layer, ensuring complete curing.

Ensure adequate ventilation during application of the membrane. In enclosed spaces, mechanical ventilation with at least 7 air changes per hour is mandatory.

CONSUMPTION:

Product	Consumption
Plex 1310 Thix	1-3 kg/m ²

CATALYST QUANTITY:

Temp. [°C]	Catalyst [%]	Processing time [min]	Cure time [min]
0 - 10	6	11	30
10 - 20	4	8	30
20 - 30	2	8	30

PROPERTIES:

Excellent crack bridging characteristics

Tough elastic and thixotropic

Easy to apply

Excellent waterproofing properties

Fully cured one hour after application

Good chemical and abrasion resistance

Very high impact and puncture resistance

TECHNICAL PARAMETERS:

Viscosity¹ [mPa·s] 4500-5500

Density² [g/cm³] 1,25 - 1,35

Shore Hardness³ > D50

Tensile strength⁴ [N/mm²] > 8

Elongation at break⁴ [%] > 200

Flashpoint⁵ + 11,5° C

1) IKA lo-vi, SP-3, 30 RPM, 20°C

2) ISO 2811-1, + 23°C/50% R.H

3) DIN 53505, 14 days / +23°C / 50% R.H

4) ISO 527/+ 23 °C/50% R.H

5) ISO 1516

PACKAGING:

Can packing: 20 kg

FORM:

Plex 1310 Thix: Liquid, brownish.

Plex 192 : Powder, white

SHELF LIFE:

Up to 6 months from the date of production in the original, tightly closed, unopened and undamaged packaging, stored in a dry place at a temperature from + 5°C to 25°C.

SUBSTRATE PREPARATION:

The substrate must be dry, clean, and free from lime and other contaminants that could reduce the adhesion strength of the applied coatings. Laitance and loose particles must be removed and the surface must be mechanically prepared, e.g., by blasting, grinding, or milling. All cracks and damages in the floor must be repaired before installation of the primer and membrane.

APPLICATION CONDITIONS:

Substrate temperature: Minimum 0°C, maximum +35 °C

Ambient temperature: Minimum 0°C, maximum +35 °C

Suitabel for use on moist substrates up to 5% residual moisture

To be tested by carbide measurement.

Relative air humidity: Maximum 95% R.H.

Dew point: Beware of condensation!

The material and substrate should be at least 3°C higher than the dew point.

REMARKS:

Wear appropriate personal protective equipment when applying the material.

Prior to use, Plex 1310 Thix must be carefully stirred to achieve a uniform distribution of agents contained in the product.

Mixed materials should be processed immediately.

LEGAL NOTICE:

This information, and in particular the recommendations related to the application and end use of Eurostep products, is provided in good faith based on our current knowledge and experience of the products. It is valid for products that are correctly stored, treated and applied under normal conditions in accordance with Eurostep's recommendations.

In practice, differences in materials, substrates and actual on-site conditions are such that no warranty in respect of merchantability or of suitability for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the products must test the product's suitability for the intended application and purpose. Eurostep reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the technical data sheet for the product concerned, copies of which will be supplied on request.

HEALTH AND SAFETY:

For information and advice on the safe handling, storage and disposal of chemical products, the user should consult the most recent product safety data sheet consult, regarding the physical, ecological, toxicological and other safety-related data.

VALUE BASE:

All technical data stated in this technical data sheet is based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

For more information about the Eurostep products or for technical advice, please contact:

Eurostep Poland Sp. z o.o.
Tymiankowa 37/39
95-054 Ksawerów
Poland

Tel.: +48 609 222 050

www.Eurostep.pl